

APPLICATION FOR U.S. PATENT

ELASTIC BLENDS COMPRISING CRYSTALLINE POLYMER AND
CRYSTALLIZABLE POLYMERS OF PROPYLENE

5

**Inventors: Sudhin Datta, Charles Cozewith, Periagaram S. Ravishankar and
Edmund J. Stachowski, III**

Field of the Invention

10

The invention relates to a blend of at least two thermoplastic components differing in their crystallinities. The blend has a heterogeneous morphology with distinct phase separated zones of different composition and crystallinity present. The resulting blend with the defined morphology shows dramatic improvements in mechanical deformation recoverability when compared to its individual unblended components. The invention also relates to improvements in the flexibility of the blend. Changes in the relative amounts or the crystallinities of the blend components or the morphology of the blend affect the recoverability and the flexibility of the blend.

15

20

The inventive blends designed for recoverability contains a dispersed phase of a greater crystallinity and a continuous phase of lesser crystallinity. The sizes of the individual domains of the dispersed phase are very small with the smallest length dimension for the dispersed phase being less than 5 μ m. This phase size of the dispersed phase is maintained during processing even without crosslinking. The inventive blends designed for flexibility have a slightly wider range in morphology as the components of greater and lesser crystallinity can also be co-continuous. The components of the blend in both cases are also compatible to the extent that no compatibilizer needs to be added to attain and retain this fine morphology.

25

Furthermore, this invention describes improving the mechanical deformation recoverability of the aforementioned blends by aging the blends and mechanically orienting the articles formed from these blends.

One of the components is a polymer comprising predominately stereospecific polypropylene, preferably isotactic polypropylene. This is the component with greater crystallinity. A second component is a copolymer of propylene and a C₂, C₃-C₂₀ α -olefin, preferably ethylene. This is the component with lesser crystallinity. In the copolymer the propylene is polymerized substantially stereospecifically. The copolymer has a substantially uniform composition distribution preferably as a result of polymerization with a metallocene catalyst. Most preferably, said second component is an ethylene propylene copolymer, e.g. ethylene propylene semicrystalline elastomer.

Background of the Invention

There is a need in the art for polymeric blends having a stereospecific polypropylene component with good tensile strength while still providing suitable mechanical recoverability (elastic recovery) and flexibility (low flexural modulus). This invention is aimed at improving the aforementioned properties of blends having a stereoregular polypropylene component, especially isotactic polypropylene. This is achieved by blending the stereoregular polypropylene component with a copolymer of propylene and a C₂, C₃-C₂₀ α -olefin. This copolymer is less crystalline than the isotactic polypropylene. In the copolymer the propylene is polymerized substantially stereospecifically. Most preferably, the copolymer is an ethylene propylene copolymer, e.g., ethylene propylene thermoplastic elastomer. The copolymer has a substantially uniform composition distribution preferably as a result of polymerization with a metallocene catalyst. Composition distribution is a property of copolymers indicating a statistically significant intermolecular or intramolecular

difference in the composition of the polymer. Methods for measuring compositional distribution are described later.

Blends of isotactic polypropylene and ethylene propylene rubber are well known in the prior art. However, the traditional Ziegler-Natta catalysts cannot make
5 ethylene propylene thermoplastic elastomers which simultaneously are uniform in compositional distribution, have substantially stereospecific propylene residues and have less than 35 wt. % ethylene.

U.S. Patent No. 3,882,197 to Fritz et al. describes blends of stereoregular propylene/alpha-olefin copolymers, stereoregular propylene, and ethylene
10 copolymer rubbers. In U.S. Patent 3,888,949 Chi-Kai Shih, assigned to E I Du Pont, shows the synthesis of blend compositions containing isotactic polypropylene and copolymers of propylene and an alpha-olefin, containing between 6 - 20 carbon atoms, which have improved elongation and tensile strength over either the copolymer or isotactic polypropylene. Copolymers of propylene and alpha-olefin
15 are described wherein the alpha-olefin is hexene, octene or dodecene. However, the copolymer is made with a heterogeneous titanium catalyst resulting in copolymers with non-uniform composition distribution and a broad molecular weight distribution. Non-uniform intramolecular compositional distribution is evident in US Patent No. 3,888,949 by the use of the term "block" in the description of the
20 polymer where the copolymer is described as having "sequences of different alpha-olefin content." Within the context of the invention described above the term sequences describes a number of olefin monomer residues linked together by chemical formed during polymerization.

In U.S. Patent 4,461,872, A.C.L. Su improved on the properties of the blends
25 described in U.S. Patent 3,888,949 by using another heterogeneous catalyst system which is expected to form copolymers which have statistically significant intermolecular and intramolecular compositional differences.

In two successive publications in the journal of *Macromolecules*, 1989, V22, pages 3851-3866, J.W. Collette of E. I. Du Pont has described blends of isotactic polypropylene and partially atactic polypropylene which have desirable tensile elongation properties. However, the partially atactic propylene has a broad molecular weight distribution as shown in Figure 8 of the first publication. The partially atactic polypropylene is also composed of several fractions, which differ in the level of tacticity of the propylene units as shown by the differences in the solubility in different solvents. This is shown by the corresponding physical decomposition of the blend which is separated by extraction with different solvents to yield individual components of uniform solubility characteristics as shown in Table IV of the above publications.

More recently several authors have shown the formation of more refined structures of partially atactic, partially isotactic polypropylene which have elastomeric properties. It is believed that in these components each molecule consists of portions which are isotactic and therefore crystallizable while the other portions of the same polypropylene molecule are atactic and therefore amorphous. Examples of these propylene homopolymers containing different levels of isotacticity in different portions of the molecule are described by R. Waymouth in U.S. Patent 5,594,080, in the article in the *Journal American Chemical Society* (1995), Vol. 117, page 11586, and in the article in the *Journal American Chemical Society* (1997), Vol. 119, page 3635, J. Chien in the journal article in the *Journal of the American Chemical Society* (1991), Vol. 113, pages 8569-8570; and S. Collins in the journal article in *Macromolecules* (1995) Vol. 28, pages 3771-3778. These articles describe a specific polymer, but do not describe the blends with a more crystalline polymer such as isotactic polypropylene.

In U.S. Patent Nos. 3,853,969 and 3,378,606, E.G. Kontos discloses the formation of *in situ* blends of isotactic polypropylene and "stereo block" copolymers

of propylene and another olefin of 2 to 12 carbon atoms, including ethylene and hexene. The copolymers of this invention are necessarily heterogeneous in intermolecular and intramolecular composition distribution. This is demonstrated by the synthesis procedures of these copolymers which involve sequential injection of monomer mixtures of different compositions to synthesize polymeric portions of analogously different compositions. In addition, Fig. 1 of both patents shows that the "stereo block" character, which is intra or intermolecular compositional differences in the context of the description of the present invention, is essential to the benefit of the tensile and elongation properties of the blend. Moreover, all of these compositions either do not meet all of the desired properties for various applications, and/or involve costly and burdensome process steps to achieve the desired results.

Similar results are anticipated by R. Holzer and K. Mehnert in U.S. Patent 3,262,992 assigned to Hercules wherein the authors disclose that the addition of a stereoblock copolymer of ethylene and propylene to isotactic polypropylene leads to improved mechanical properties of the blend compared to isotactic polypropylene alone. However, these benefits are described only for the stereoblock copolymers of ethylene and propylene. These copolymers were synthesized by changing the monomer concentrations in the reactor with time. This is shown in examples 1 and 2. The stereoblock character of the polymer is graphically shown in the molecular description (column 2, line 65) and contrasted with the undesirable random copolymer (column 2, line 60). The presence of stereoblock character in these polymers is shown by the high melting point of these polymers and the poor solubility in hydrocarbons at ambient temperature.

There is a need for a polyolefin blend composition which is thermally stable, heat resistant, light resistant and generally suitable for thermoplastic elastomer (TPE) applications which has advantageous processing characteristics. We have

found that by blending a crystalline propylene polymer, hereinafter referred to as the "first polymer component, (FPC)" and a crystallizable propylene alpha olefin copolymer polymer, hereinafter referred to as the "second polymer component (SPC)", advantageous processing characteristics result while still providing a composition having decreased flexural modulus and increased tensile strength, elongation, recovery and overall toughness. It is possible to have the addition of a third polymeric component which is another crystallizable propylene alpha olefin copolymer indicated as SPC2 in the text below which has crystallinity intermediate between the FPC and the SPC. The SPC2 also has a narrow composition distribution and is made with a metallocene catalyst. The addition of SPC2 leads to a finer morphology and improvements in some of the properties of the blend of FPC and SPC.

The term "crystalline," as used herein for FPC, characterizes those polymers which possess high degrees of inter- and intra-molecular order, and which melt higher than 110°C and preferably higher than 115°C and more preferably higher than 130°C and preferably have a heat of fusion of at least 75 J/g, as determined by DSC analysis. And, the term "crystallizable," as used herein for SPC describes polymers which are mainly amorphous in the undeformed state, but can crystallize upon stretching or annealing. Crystallization may also be initiated by the presence of a crystalline polymer such as the FPC. These polymers have a melting point of less than 105° C or preferably less than 100°C and preferably have a heat of fusion of less than 75 J/g as determined by DSC. SPC2 describes those polymers that are substantially crystalline in the undeformed state. Further crystallization may also occur in the presence of the crystalline polymer such as FPC. These polymers have a melting point of less than 115° C or preferably less than 100°C and preferably have a heat of fusion of less than 75 J/g as determined by DSC.

Summary of the Invention

The present invention is directed to blends with heterophase morphology formed by blending a FPC which is a predominately crystalline stereoregular polypropylene with a SPC which is a crystallizable copolymer of a C₂, C₄-C₂₀ α-olefin (preferably ethylene) and propylene . Optional components of the blend are
5 SPC2, a crystallizable copolymer of a C₂, C₄-C₂₀ α-olefin (preferably ethylene), and process oil. Other optional components are fillers, colorants, antioxidants, nucleators and flow improvers.

The FPC melts higher than 110°C and preferably higher than 115°C and
10 more preferably higher than 130°C and preferably has a heat of fusion of at least 75 J/g, as determined by DSC analysis. The crystalline polypropylene can be either homopolymer or copolymers with other alpha olefins. The FPC may also be comprised of commonly available isotactic polypropylene compositions referred to as impact copolymer or reactor copolymer. However these variations in the identity
15 of the FPC are acceptable in the blend only to the extent that the FPC is within the limitations of the crystallinity and melting point indicated above. The FPC may also contain additives such as flow improvers, nucleators and antioxidants which are normally added to isotactic polypropylene to improve or retain properties. All of these polymers are referred to as the FPC.

20 The SPC and the SPC2, if used, have stereoregular propylene sequences long enough to crystallize. The SPC has a melting point of less than 105°C or preferably less than 100°C and preferably has a heat of fusion of less than 75 J/g. The SPC2 has a melting point of less than 115° C or preferably less than 100°C and preferably has a heat of fusion of less than 75 J/g. These stereoregular propylene sequences of SPC
25 and SPC2 should substantially match the stereoregularity of the propylene in the first polymer. For example, if the FPC is predominately isotactic polypropylene, then the SPC, and SPC2 if used, is copolymer having isotactic propylene sequences.

If the FPC is predominately syndiotactic polypropylene, then the SPC, and the SPC2 if used, is a copolymer having syndiotactic sequences. Therefore, SPC and SPC2 have similar, preferably substantially identical, tacticity to the FPC. It is believed that this matching of stereoregularity increases the compatibility of the components and results in improved adhesion at the interface of the domains of the polymers of different crystallinities in the polymer blend composition. Furthermore, good compatibility is only achieved in a narrow range of copolymer composition for the SPC. Narrow intermolecular and intramolecular compositional distribution in the copolymer is preferred. The aforementioned characteristics of the SPC, and SPC2 if used, are preferably achieved by polymerization with a chiral metallocene catalyst.

One preferable embodiment is blending isotactic polypropylene (FPC) with ethylene propylene copolymers (SPC) having about 4 wt. % to about 35 wt. % ethylene (to ensure high compatibility with the FPC). Both the FPC and the SPC have isotactic propylene sequences long enough to crystallize. Resulting blends of isotactic polypropylene with ethylene propylene copolymers according to the invention have improved properties as compared to isotactic polypropylene blends with prior art ethylene propylene rubbers.

A preferred blend comprises 1% to 95% by weight of FPC and a SPC with greater than 65% by weight propylene and preferably greater than 80% by weight propylene.

According to another embodiment, a thermoplastic polymer blend composition of the invention comprises a FPC and a SPC with added process oil. The FPC comprises isotactic polypropylene, a reactor copolymer or an impact copolymer as described above and is present in an amount of about 1% to about 95% by weight and more preferably 2% to 70% by weight of the total weight of the blend. The balance of the polymer composition consists of a mixture of the process oil and the SPC and SPC2 if used

The SPC is a random copolymer of ethylene and propylene having a melting point by DSC of 0°C to 105°C, preferably in the range 20°C to 90°C, more preferably in the range of 25°C to 70°C and an average propylene content by weight of at least 65% and more preferably at least 80%. This melting point is due to crystallizable propylene sequences, preferably of isotactic polypropylene. The SPC is made with a polymerization catalyst which forms essentially or substantially isotactic polypropylene, when all or substantially all propylene sequences in the FPC are isotactic. The SPC is statistically random in the distribution of the ethylene and propylene residues along the chain. Quantitative evaluation of the randomness of the distribution of the ethylene and propylene sequences may be obtained by consideration of the experimentally determined reactivity ratios of the second polymer component or by ¹³C NMR. This is according to the procedures described in the journal article by H. Kakugo, Y Naito, K. Mizunama and T. Miyatake in *Macromolecules* (1982), pages 1150-1152. The SPC is made with a single sited metallocene catalyst which allows only a single statistical mode of addition of ethylene and propylene by polymerization in a well mixed, continuous feed stirred tank reactor which provides a uniform polymerization environment for growth of all of the polymer chains of the SPC.

The ratio of the FPC to the SPC of the blend composition of the present invention may vary in the range of 1:99 to 95:5 by weight and more preferably in the range 2:98 to 70:30 by weight.

According to another embodiment of the present invention, the second polymer component may contain small quantities of a non-conjugated diene to aid in the vulcanization and other chemical modification of the blend of the first polymer component and the second polymer component. The amount of diene is preferably less than 10 wt. % and preferably less than 5 wt. %. The diene may be selected from the group consisting of those which are used for the vulcanization of ethylene

propylene rubbers and are preferably ethylidene norbornene, vinyl norbornene and dicyclopentadiene.

The SPC2, if used, has the same characteristics as the SPC described above. The SPC2 has a crystallinity and composition intermediate between the FPC and the SPC. In the preferred case where the SPC2 is a copolymer of ethylene and propylene while the FPC is homopolymer of propylene. The SPC2 has the same type of crystallinity of propylene as in the FPC and SPC and an ethylene content in between FPC and SPC. The addition of SPC2 to the blend leads to a better dispersion of the phases in the blend compared to blends of the similar composition which do not have any SPC2. The relative amounts of SPC and SPC2 can vary between 95:5 to 10:90 in the blend. The ratio of the FPC to the sum of SPC and SPC2 may vary in the range of 1:99 to 95:5 by weight and more preferably in the range 2:98 to 70:30 by weight

According to still a further embodiment, the invention is directed to a process for preparing thermoplastic polymer blend compositions. The process comprises: (a) polymerizing propylene or a mixture of propylene and one or more monomers selected from C_2 or $C_3 - C_{20}$ α -olefins in the presence of a polymerization catalyst wherein a substantially isotactic propylene polymer containing at least about 90% by weight polymerized propylene is obtained; (b) polymerizing a mixture of ethylene and propylene in the presence of a chiral metallocene catalyst, wherein a copolymer of ethylene and propylene is obtained comprising up to about 35% by weight ethylene and preferably up to 20% by weight ethylene and containing isotactically crystallizable propylene sequences; and (c) blending the propylene polymer of step (a) with the copolymer of step (b) to form a blend.

The invention is directed to the formation of a blend of the components FPC, SPC and SPC2 which has a heterogeneous phase morphology consisting of domains of different crystallinities. Blends directed to improvement in the elastic recovery

have a continuous phase of lower crystallinity and a dispersed phase of the higher crystallinity. The domains of the dispersed phase are small with an average minimum axis less than 5 μ m. The larger axis of the dispersed phase can be as large as 100 μ m. The dispersed phase consists of a crystalline mixture of FPC with some amount of SPC2 and SPC due to thermodynamic mixing of polymers. The continuous phase consists of the balance of the polymers not included in the dispersed phase. Blends directed to low flexural modulus may have in addition, a heterogeneous phase morphology with continuous phases of lower and greater crystallinity.

Commonly available propylene reactor copolymers consisting of a single phase blend of isotactic polypropylene and copolymers of propylene and ethylene are not included within the scope of the invention since they are a single phase with no prominent dispersed or continuous phases. Polypropylene blends made by a combination of a FPC and a SPC of the present invention that give a heterophase morphology in which the crystalline polymer is the continuous phase in are excluded from the invention.

The benefits of the invention are included improvement in the elastic recovery and the flexural modulus of the blend. These improvements are most apparent as a function of the 500% tensile modulus of the blend. Historically, the examples of the prior art have been able to duplicate the improvements in the blend but only for compositions with a very low 500% tensile modulus

Brief Description of the Drawings

Figure 1 shows the morphology of a blend of this invention. Specifically, Figure 1 shows the morphology of sample H7 in Example 6 below.

Figure 2 shows the morphology of a blend of this invention. Specifically, Figure 2 shows the morphology of sample K7 in Example 6 below.

Figure 3 shows the morphology of a blend of this invention which includes SPC2. Specifically, Figure 3 shows the morphology of sample BB7 in Example 6 below.

5 Figure 4 and Figure 5 show the stress strain elongation data for blends of this invention.

Figure 6 shows the elastic recovery of annealed/aged blends of this invention.

Figure 7 shows the elastic recovery of oriented blends of this invention.

10 Figure 8 shows the dependence of the flexural modulus of the blend of this invention as a correlated function of the 500% tensile modulus.

Detailed Description of the Preferred Embodiments of the Invention

The blend compositions of the present invention generally are comprised of two components: (1) a crystalline FPC comprising isotactic polypropylene and (2) a crystallizable SPC comprising an alpha-olefin (other than propylene) and propylene copolymer. A particular embodiment of the invention contains a crystallizable SPC2 comprising an alpha-olefin (other than propylene) and propylene copolymer. A particular embodiment of the invention may comprise process oil as an additional component.

15

20

The blend also has a heterogeneous phase morphology where a more crystalline polymer mixture consisting essentially of all the FPC and some of the SPC and SPC2 is dispersed in domains in a continuous phase of a less crystalline polymer mixture containing the balance of the blend. The size of the dispersed domains is small and the morphology is stable in the absence of a compatibilizer. Preferably, compositions of the invention are free of, or substantially free of, compatibilizers.

25

The First Polymer Component (FPC)

In accordance with the present invention, the FPC component i.e., the polypropylene polymer component may be homopolypropylene, or copolymers of propylene, or some mixtures thereof. The FPC has the following characteristics.

5 (A) The polypropylene of the present invention is predominately crystalline, i.e., it has a melting point generally greater than about 110°C, preferably greater than about 115°C, and most preferably greater than about 130°C. Preferably, it has a heat of fusion greater than 75 J/g.

10 (B) The polypropylene can vary widely in composition. For example, substantially isotactic polypropylene homopolymer or propylene copolymer containing equal to or less than about 10 weight percent of other monomer, i.e., at least about 90% by weight propylene can be used. Further, the polypropylene can be present in the form of a graft or block copolymer, in which the blocks of polypropylene have substantially the same stereoregularity as the propylene-alpha-olefin copolymer, so long as the graft or block copolymer has a sharp melting point
15 above about 110°C, preferably above 115°C, and more preferably above 130°C, characteristic of the stereoregular propylene sequences. The propylene polymer component may be a combination of homopolypropylene, and/or random, and/or block copolymers as described herein. When the above propylene polymer
20 component is a random copolymer, the percentage of the copolymerized alpha-olefin in the copolymer is, in general, up to about 9% by weight, preferably about 2% to about 8% by weight, most preferably about 2% to about 6% by weight. The preferred alpha-olefins contain 2 or from 4 to about 12 carbon atoms. The most preferred alpha-olefin is ethylene. One or two or more alpha-olefins can be
25 copolymerized with propylene.

Exemplary alpha-olefins may be selected from the group consisting of ethylene; butene-1; pentene-1,2-methylpentene-1,3-methylbutene-1; hexene-1,3-

methylopentene-1,4-methylopentene-1,3,3-dimethylbutene-1; heptene-1; hexene-1; methylhexene-1; dimethylpentene-1 trimethylbutene-1; ethylpentene-1; octene-1; methylpentene-1; dimethylhexene-1; trimethylpentene-1; ethylhexene-1; methylethylpentene-1; diethylbutene-1; propylpentane-1; decene-1; methylnonene-1; nonene-1; dimethyloctene-1; trimethylheptene-1; ethyloctene-1; methylethylbutene-1; diethylhexene-1; dodecene-1 and hexadodecene-1.

(C) The molecular weight of the FPC can be between 10,000 to 5,000,000 with a polydispersity index (PDI) between 1.5 to 40.0

(D) The thermoplastic polymer blend compositions of the present invention may comprise from about 1% to about 95% by weight of FPC. According to a preferred embodiment, the thermoplastic polymer blend composition of the present invention may comprise from about 2% to about 70% by weight of the FPC. According to the most preferred embodiment, the compositions of the present invention may comprise from about 2% to about 40% by weight of the FPC. An even more preferred embodiment of the invention contains 2% to 25% by weight of FPC in the blend.

There is no particular limitation on the method for preparing this propylene polymer component of the invention. However, in general, the polymer is a propylene homopolymer obtained by homopolymerization of propylene in a single stage or multiple stage reactor. Copolymers may be obtained by copolymerizing propylene and an alpha-olefin having 2 or from 4 to about 20 carbon atoms, preferably ethylene, in a single stage or multiple stage reactor. Polymerization methods include high pressure, slurry, gas, bulk, or solution phase, or a combination thereof, using a traditional Ziegler-Natta catalyst or a single-site, metallocene catalyst system. The catalyst used is preferably one which has a high isospecificity. Polymerization may be carried out by a continuous or batch process and may include

use of chain transfer agents, scavengers, or other such additives as deemed applicable.

The Second Polymer Component (SPC)

5 The SPC of the polymer blend compositions of the present invention comprises a crystallizable copolymer of propylene and another alpha-olefin having less than 10 carbon atoms, preferably ethylene. The SPC has the following characteristics:

10 (A) The SPC of the present invention preferably comprises a random copolymer having a narrow compositional distribution. While not meant to be limited thereby, it is believed that the narrow composition distribution of the second polymer component is important. The intermolecular composition distribution of the polymer is determined by thermal fractionation in a solvent. A typical solvent is a saturated hydrocarbon such as hexane or heptane. This thermal fractionation
15 procedure is described below. Typically, approximately 75% by weight and more preferably 85% by weight of the polymer is soluble in one or two adjacent fractions with the balance of the polymer in immediately preceding or succeeding fractions. Each of these fractions has a composition (wt. % ethylene content) with a difference of no greater than 20 wt. % (relative) and more preferably 10 wt. % (relative) of the
20 average wt. % ethylene content of the whole second polymer component. The second polymer component is narrow in compositional distribution if it meets the fractionation test outlined above.

 (B) In all SPC, the length and distribution of stereoregular propylene sequences is consistent with the substantially random statistical copolymerization. It
25 is well known that sequence length and distribution are related to the copolymerization reactivity ratios. By substantially random, we mean copolymer for which the product of the reactivity ratios is 2 or less. In stereoblock structures, the

average length of PP sequences is greater than that of substantially random copolymers with a similar composition. Prior art polymers with stereoblock structure have a distribution of PP sequences consistent with these blocky structures rather than a random substantially statistical distribution. The reactivity ratios and
5 sequence distribution of the polymer may be determined by C-13 NMR which locates the ethylene residues in relation to the neighboring propylene residues. To produce a copolymer with the required randomness and narrow composition distribution, it is desirable to use (1) a single sited catalyst and (2) a well-mixed, continuous flow stirred tank polymerization reactor which allows only a uniform
10 polymerization environment for growth of substantially all of the polymer chains of the second polymer component.

(C) The SPC preferably has a single melting point. The melting point is determined by DSC. Generally, the SPC of the present invention has a melting point between about 105°C and 0°C. Preferably, the melting point of SPC is between
15 about 90°C and 20°C. Most preferably, according to one embodiment of the present invention, the melting point of the SPC of the composition of the present invention is between 70°C and 25°C.

(D) The second polymer component of the present inventive composition comprises crystallizable propylene sequences. The crystallinity of the second
20 polymer component is, preferably, according to one embodiment, from about 1% to about 65% of homoisotactic polypropylene, preferably between 3% to 30%, as measured by the heat of fusion of annealed samples of the polymer.

(E) The molecular weight of the SPC can be between 10,000 to 5,000,000 with a polydispersity index (PDI) between 1.5 to 40.0. The second polymer
25 component preferably has a narrow PDI between about 1.8 to about 5. It is preferred if the SPC has a Mooney Viscosity at 125°C less than 100, more preferably less than 75 and more preferably less than 60.

(F) The low levels of crystallinity in the SPC are obtained by incorporating from about 5% to about 35% by weight alpha-olefin, preferably from about 6% to about 30% by weight alpha-olefin, and most preferably, it comprises from about 8% to about 25% by weight alpha-olefin and even more preferably between 8% to 20% by alpha-olefin. These composition ranges for the SPC are preferred to obtain the objectives of the present invention. Alpha olefins comprise one or more members of the group C₂, C₄-C₂₀ α-olefin. At alpha-olefin compositions lower than the above lower limits for the composition of the SPC, the blends of the FPC and SPC are thermoplastic and do not have the phase separated morphology required for the tensile recovery properties of the blends. At alpha-olefin compositions higher than the above higher limits for the SPC, the blends have poor tensile strength and a phase separated morphology with a coarse dispersion. It is believed, while not meant to be limited thereby, the SPC needs to have the optimum amount of polypropylene crystallinity to crystallize with the FPC for the beneficial effects of the present invention. As discussed above, the preferred alpha-olefin is ethylene.

(G) The compositions of the present invention may comprise from about 5% to about 99% by weight of the SPC and from about 30% to about 98% by weight of the SPC. Most preferably, they comprise from about 60% to about 98% and even more preferably 75% to 99% by weight of the SPC.

(H) More than one SPC may be used in a single blend with a FPC. Each of the SPC is described above and the number of SPC in this embodiment is less than three and more preferably, two. The different SPC differ in the crystallinity. For two SPC components, the SPC2 is more crystalline than the SPC. The SPC2 has, preferably, according to one embodiment, from about 20% to about 65%, and more preferably between 25% to 65% of the crystallinity of homoisotactic polypropylene as measured by the heat of fusion of annealed samples of the polymer. The SPC and the SPC2 may also differ in their molecular weight. The SPC and SPC2 differ in the

alpha-olefin content consistent with the use of two SPC with different crystallinity. The preferred alpha-olefin is ethylene. It is believed that the use of SPC2 in conjunction with a blend of a FPC and a SPC acts as an interfacial agent in these blends. The resultant morphology consists of a finer dispersion of the highly crystalline component with the continuous phase of the less crystalline phase. Such a morphology leads to in the elastic recovery properties of the blends.

The second polymer component may also comprise a copolymer of atactic propylene and isotactic propylene. Such crystallizable homopolymers of propylene have been described by R. Waymouth in U. S. Patent 5,594,080, which is included herein by reference. Optionally, the second component of the composition of the present invention may comprise a diene.

(I) The SPC and the SPC2, if used, have stereoregular propylene sequences long enough to crystallize. These stereoregular propylene sequences of SPC and SPC2 should match the stereoregularity of the propylene in the second polymer. For example, if the FPC is predominately isotactic polypropylene, then the SPC, and SPC2 if used, are copolymers having isotactic propylene sequences. If the FPC is predominately syndiotactic polypropylene, then the SPC, and the SPC2 if used, is a copolymer having syndiotactic sequences. It is believed that this matching of stereoregularity increases the compatibility of the components results in improved adhesion of the domains of the polymers of different crystallinities in the polymer blend composition. Furthermore, good compatibility is only achieved in a narrow range of copolymer composition for the SPC. Narrow intermolecular and intramolecular compositional distribution in the copolymer is preferred. The aforementioned characteristics of the SPC, and SPC2 if used, are preferably achieved by polymerization with a chiral metallocene catalyst.

(J) The SPC is made with a polymerization catalyst which forms essentially or substantially isotactic polypropylene when all or substantially all propylene

sequences in the FPC are isotactic. Nonetheless, the polymerization catalyst used for the formation of SPC will introduce stereo- and regio- errors in the incorporation of propylene. Stereo errors are those where the propylene inserts in the chain with a tacticity that is not isotactic. A regio error is one where the propylene inserts with the methylene group or the methyldiene group adjacent to a similar group in the propylene inserted immediately prior to it. Such errors are more prevalent after the introduction of an ethylene in the SPC. Thus, the fraction of propylene in isotactic stereoregular sequences (e.g. triads or pentads) is less than 1 for SPC and decreases with increasing ethylene content of the SPC. While not wanting to be constrained by this theory, we suggest that the introduction of these errors in the introduction of propylene, particularly in the presence of increasing amounts of ethylene, are important in the use of these ethylene propylene copolymers as the SPC. Notwithstanding the presence of these errors, the SPC is statistically random in the distribution of ethylene.

(K) The SPC is made with a polymerization catalyst which forms essentially or substantially isotactic polypropylene, when all or substantially all propylene sequences in the FPC are isotactic. The SPC is statistically random in the distribution of the ethylene and propylene residues along the chain. Quantitative sequences may be obtained by consideration of the experimentally determined reactivity ratios of the second polymer component or by ^{13}C NMR. The SPC is made with a single sited metallocene catalyst which allows only a single statistical mode of addition of ethylene and propylene in a well-mixed, continuous monomer feed stirred tank polymerization reactor which allows only a single polymerization environment for all of the polymer chains of the SPC.

Generally, without limiting in any way the scope of the invention, one means for carrying out a process of the present invention for the production of the copolymer second polymer component is as follows: (1) liquid propylene is

introduced in a stirred-tank reactor, (2) the catalyst system is introduced via nozzles in either the vapor or liquid phase, (3) feed ethylene gas is introduced either into the vapor phase of the reactor, or sparged into the liquid phase as is well known in the art, (4) the reactor contains a liquid phase composed substantially of propylene, together with dissolved alpha-olefin, preferably ethylene, and a vapor phase containing vapors of all monomers, (5) the reactor temperature and pressure may be controlled via reflux of vaporizing propylene (autorefrigeration), as well as by cooling coils, jackets, etc., (6) the polymerization rate is controlled by the concentration of catalyst, temperature, and (7) the ethylene (or other alpha-olefin) content of the polymer product is determined by the ratio of ethylene to propylene in the reactor, which is controlled by manipulating the relative feed rates of these components to the reactor.

For example, a typical polymerization process consists of a polymerization in the presence of a catalyst comprising a chiral bis (cyclopentadienyl) metal compound and either 1) a non-coordinating compatible anion activator, or 2) an alumoxane activator. An exemplary catalyst system is described in U.S. Patent No. 5,198,401 which is herein incorporated by reference for purposes of U.S. practices. The alumoxane activator is preferably utilized in an amount to provide a molar aluminum to metallocene ratio of from about 1:1 to about 20,000:1 or more. The non-coordinating compatible anion activator is preferably utilized in an amount to provide a molar ratio of biscyclopentadienyl metal compound to non-coordinating anion of 10:1 to about 1:1. The above polymerization reaction is conducted by reacting such monomers in the presence of such catalyst system at a temperature of from about -50°C to about 200°C for a time of from about 1 second to about 10 hours to produce a copolymer having a weight average molecular weight of from about 5,000 or less to about 1,000,000 or more and a molecular weight distribution of from about 1.8 to about 4.5.

While the process of the present invention includes utilizing a catalyst system in the liquid phase (slurry, solution, suspension or bulk phase or combination thereof), gas phase polymerization can also be utilized. When utilized in a gas phase, slurry phase or suspension phase polymerization, the catalyst systems will preferably be supported catalyst systems. See, for example, U.S. Patent No. 5,057,475 which is incorporated herein by reference for purposes of U.S. practice. Such catalyst systems can also include other well-known additives such as, for example, scavengers. See, for example, U.S. Patent No. 5,153,157 which is incorporated herein by reference for purposes of U.S. practices. These processes may be employed without limitation of the type of reaction vessels and the mode of conducting the polymerization. As stated above, and while it is also true for systems utilizing a supported catalyst system, the liquid phase process comprises the steps of contacting ethylene and propylene with the catalyst system in a suitable polymerization diluent and reacting the monomers in the presence of the catalyst system for a time and at a temperature sufficient to produce an ethylene-propylene copolymer of the desired molecular weight and composition.

Process oil

Process oil can be optimally added to the polymer blend compositions of the present invention. The addition of process oil in moderate amounts lowers the viscosity and flexibility of the blend while improving the properties of the blend at temperatures near and below 0°C. It is believed that these benefits arise by the lowering of the T_g of the blend comprising the mixture of the FPC and the SPC. Additional benefits of adding process oil to the blend of the FPC and the SPC include improved processability and a better balance of elastic and tensile strength are anticipated.

The process oil is typically known as extender oil in the rubber application practice. The process oils can consist of (a) hydrocarbons consisting of essentially of carbon and hydrogen with traces of heteroatoms such as oxygen or (b) essentially of carbon, hydrogen and at least one heteroatom such as dioctyl phthalate, ethers and polyethers. The process oils have a boiling point to be substantially involatile at 200°C. These process oils are commonly available either as neat solids or liquids or as physically absorbed mixtures of these materials on an inert support (e.g. clays, silica) to form a free flowing powder. We believe that all forms of these process oils are equally applicable to the description and the practice of the invention.

The process oils usually include a mixture of a large number of chemical compounds which may consist of linear, acyclic but branched, cyclic and aromatic carbonaceous structures. Another family of process oils are certain low to medium molecular weight (Molecular weight (M_n) <10,000) organic esters and alkyl ether esters. Examples of process oils are Sunpar[®] 150 and 220 from The Sun Manufacturing Company of Marcus Hook, PA, USA and Hyprene[®] V750 and Hyprene V1200 from Ergon, Post Office Box 1639, Jackson, MS 39215-1639, USA. and IRM 903 from Calumet Lubricants Co., 10234 Highway 157, Princeton, LA 71067-9172, USA. It is also anticipated that combinations of process oils each of which is described above may be used in the practice of the invention. It is important that in the selection of the process oil be compatible or miscible with the polymer blend composition of the FPC and the SPC in the melt to form a homogenous one phase blend. It is also preferred if the process oil is substantially miscible in the SPC at room temperature.

The addition of the process oils to the mixture comprising the FPC and the SPC maybe made by any of the conventional means known to the art. These include the addition of all or part of the process oil prior to recovery of the polymer as well as addition of the process oil, in whole or in part, to the polymer as a part of a

compounding for the interblending of the FPC and the SPC. The compounding step may be carried out in a batch mixer such as a mill or an internal mixer such as Banbury mixer. The compounding operation may also be conducted in a continuous process such as a twin screw extruder.

5 The addition of certain process oils to lower the glass transition temperature of blends of isotactic polypropylene and ethylene propylene diene rubber has been described in the art by Ellul in US Patents 5 290 886 and 5 397 832. We expect these procedures are easily applicable to the FPC and SPC mixtures of the current invention.

10 The FPC and SPC physical mixture may include process oil in the range of from about 1 to about 200, preferably in the range of from about 2 to 50 parts by weight of process oil per hundred parts of total polymer (FPC plus SPC).

The Blend of First and Second Polymer Components

15 The blends of FPC and SPC and other components may be prepared by any procedure that guarantees an intimate mixture of the components. For example, the components can be combined by melt pressing the components together on a Carver press to a thickness of about 0.5 millimeter (20 mils) and a temperature of about 180°C, rolling up the resulting slab, folding the ends together, and repeating the
20 pressing, rolling, and folding operation about 10 times. Internal mixers are particularly useful for solution or melt blending. Blending at a temperature of about 180°C to 240°C in a Brabender Plastograph for about 1 to 20 minutes has been found satisfactory. Still another method that may be used for admixing the components involves blending the polymers in a Banbury internal mixer above the
25 flux temperature of all of the components, e.g., 180°C for about 5 minutes. A complete mixture of the polymeric components is indicated by the uniformity of the morphology of the dispersion of FPC and SPC. Continuous mixing may also be

used. These processes are well known in the art and include single and twin screw mixing extruders, static mixers for mixing molten polymer streams of low viscosity, impingement mixers, as well as other machines and processes, designed to disperse the first polymer component and the second polymer component in intimate contact.

5 The polymer blends of the instant invention exhibit a remarkable combination of desirable physical properties. The incorporation of as little as 5% FPC in the SPC composed of propylene/alpha-olefin copolymers increases the melting point of the blend. In addition, the incorporation of FPC in accordance with the instant invention nearly eliminates the stickiness characteristic of the
10 propylene/alpha-olefin copolymer alone.

 The mechanism by which the desirable characteristics of the present copolymer blends are obtained is not fully understood. However, it is believed to involve a co-crystallization phenomenon between propylene sequences of similar stereoregularity in the various polymeric components, which results in a narrowing
15 of the differences in the crystallization temperature of the blend components. The combined first polymer component and second polymer component have a blend melting point closer together than would be expected on a comparison of the properties of the individual components alone. Surprisingly, some blend compositions have a single crystallization temperature and a single melting
20 temperature, since it would be expected by those skilled in the art that the blending of two crystalline polymers would result in a double crystallization temperature as well as a double melting temperature reflecting the two polymeric components. However, the intimate blending of the polymers having the required crystallinity characteristics apparently results in a crystallization phenomenon that modifies the
25 other physical properties of the propylene/alpha-olefin copolymer, thus measurably increasing its commercial utility and range of applications.

While the above discussion has been limited to the description of the invention in relation to having only components one and two, as will be evident to those skilled in the art, the polymer blend compositions of the present invention may comprise other additives. Various additives may be present to enhance a specific property or may be present as a result of processing of the individual components. Additives which may be incorporated include, for example, fire retardants, antioxidants, plasticizers, pigments, vulcanizing or curative agents, vulcanizing or curative accelerators, cure retarders, processing aids, flame retardants, tackifying resins, and the like. These compounds may include fillers and/or reinforcing materials. These include carbon black, clay, talc, calcium carbonate, mica, silica, silicate, combinations thereof, and the like. Other additives which may be employed to enhance properties include antiblocking agents, coloring agent. Lubricants, mold release agents, nucleating agents, reinforcements, and fillers (including granular, fibrous, or powder-like) may also be employed. Nucleating agents and fillers tend to improve rigidity of the article. The list described herein is not intended to be inclusive of all types of additives which may be employed with the present invention. Upon reading this disclosure, those of skill in the art will appreciate other additives may be employed to enhance properties of the composition. As is understood by the skilled in the art, the polymer blend compositions of the present invention may be modified to adjust the characteristics of the blend as desired.

Morphology of the blend

The morphology of the blend is shown in Transmission Electron Microscopy of the blends. In this procedure samples were exposed to vapors of 1% aqueous RuO₄ for 3 days. The RuO₄ penetrates the amorphous zones of the continuous, less crystalline phase of the polymer while the more crystalline domains composed largely of the FPC are essentially unaffected. Within the continuous zone the RuO₄

stained the microzones of amorphous polymer while the lamellae of crystalline polymer are visible by contrast. The blend was cryomicrotomed at -196°C to thin sections approximately 0.3 to $3\text{ }\mu\text{m}$ thick. Several sections were analyzed for each sample until a section was found where the crystalline domains was unstained while the continuous phase was stained to distinguish it from the dispersed phase and to observe the microstructure of the lamellae of polymer.

The blends of the current invention with good elastic recovery from tensile deformation had a microstructure with clearly dispersed microdomains of the crystalline phase. This is shown in Figure 1. The composition and elastic recovery properties of the blend is shown as H7 in the Tables below. The domains are elongated with approximate dimensions of $0.2\text{ }\mu\text{m} \times 1\text{ }\mu\text{m}$. Figure 2 shows a different blend of the invention, designated as K7 in the Tables below, with the dispersed phase having dimensions of $0.6\mu\text{m} \times 2.0\mu\text{m}$. The addition of SPC2 to this blend is shown in the micrograph BB7 (Figure 3) shows the reduction in the size of the dispersed phase to elongated particles having $0.2\mu\text{m}$ for each dimension. SPC2 is therefore believed to act as an agent for reducing the size of the dispersion of the crystalline phases in the dispersed continuous phase. This is the morphological effect of adding SPC2 to the blend of a FPC and SPC.

Properties of the blend: Elongation

The blends of the current invention have tensile elongation in excess of 700%. This elongation is determined for blends at 20in/min according to the procedure described in ASTM D790. The data is reported in engineering units with no correction to the stress for the lateral contraction in the specimen due to tensile elongation.

The stress-strain elongation properties of the insitu and the corresponding physical blends was evaluated using dumbbell shaped sample. The samples were

compression molded at 180° C to 200° C for 15 minutes at a force of 15 tons into a plaque of dimensions of 6 in x 6 in. The cooled plaques were removed and the specimens were removed with a die. The stress strain evaluation of the samples was conducted on an Instron 4465 tester, made by Instron Corporation of 100 Royall Street, Canton, MA. The digital data was collected in a file collected by the Series IX Material Testing System available from Instron Corporation and analyzed using Excel 5, a spreadsheet program available from Microsoft Corporation of Redmond, WA.

Figure 4 and Figure 5 show the stress strain elongation data for blends containing one FPC and one SPC or two SPC respectively.

Properties of the Blend: Elastic Recovery

The benefit of the above invention is that compositions comprising the FPC and the SPC optionally containing SPC2 and/or amounts of process oil can be made which have excellent elastic recovery from tensile deformation. These elastic blends have a morphology of containing a crystalline phase dispersed in the continuous crystallizable phase. The dispersed crystalline phase contains the majority of the FPC and some of the SPCs due to thermodynamic mixing while the continuous phase consists of the balance of the polymer blend. Elastic recovery from tensile deformation is a tension set from 200% extension of less than 40%, more preferably less than 25% and more preferably less than 15%.

These values of the tension set over the range of composition of the FPC and SPC are dependent on the 500% tensile modulus. Elastic recovery of the blend is judged on two criteria: (a) extensibility to 500% elongation with a measurable modulus and (b) tension set from an extension to 200% elongation. Comparative blends often cannot be extended to 500% extension for evaluation of the 500% modulus and, thus, cannot be compared to the blends of the current invention. Some

comparative blends in the prior art can be extended to 500% elongation for the measurement of tensile modulus but have poor elastic recovery from a 200% extension. The elastic blends of the current invention fulfill both of these conditions. Generally for all blends the tension set deteriorates with increase in the 500% tensile modulus. Thus tension set from a 200% extension is judged relative to the tensile modulus of the blend for a 500% extension. The blends of the current invention have better elastic recovery, as indicated by low tension set, than blends of the comparative blends at comparable 500% tensile modulus. These properties are available over a wide range of composition and relative amounts of the FPC and the SPC. These compositions also have a range of tensile strength from 300psi to 5000psi. In the examples shown below, we show examples of numerous blends of composition of the FPC and the SPC which have the above favorable combination of properties.

In one embodiment, the composition of the invention has a tension set from 200% extension equal to or less than $0.02M + 5$, preferably equal to or less than $0.0108M + 3$, more preferably equal to or less than $0.0052M + 2$, wherein M is 500% modulus expressed in lbs/inch^2 .

It is possible to generate comparative polymer blends with some aspect of the combined 500% tensile modulus and 200% tension set properties of the blends of this invention approached if the SPCs are of extremely high molecular weight and in the limit crosslinked. Such a combination would lead to blends which had very poor processing characteristics since they would tend to melt fracture. It is understood that those polymer blends are directed to easy processing materials that can be handled in conventional thermoplastics processing machinery.

Another part of the invention is that the elastic recovery referred to above can be enhanced by the thermal annealing of the polymer blends or by the orientation of articles made from these polymer blends. Thermal annealing of the polymer blend is

conducted by maintaining the polymer blends or the articles made from a such a blend at temperature between room temperature to a maximum of 160°C or more preferably to a maximum of 130°C for a period between 5 minutes to less than 7 days. A typical annealing period is 3 days at 50°C or 5 minutes at 100°C. The annealing time and temperature can be adjusted for any particular blend composition comprising a FPC and one or two SPC by experimentation. It is believed that during this annealing process, there is intermolecular rearrangement of the polymer chains, leading to a material with much greater recovery from tensile deformation than the unannealed material. The elastic recovery of annealed/aged blends of this invention is shown in Figure 6.

Another part of the invention is that the mechanical properties referred to above can be enhanced by the mechanical orientation of the polymer blend. Mechanical orientation can be done by the temporary, forced extension of the polymer blend along one or more axis for a short period of time before it is allowed to relax in the absence of the extensional forces. It is believed that the mechanical orientation of the polymer leads to reorientation of the crystallizable portions of the blend of the first and the second polymer. Oriented polymer blends is conducted by maintaining the polymer blends or the articles made from a such a blend at an extension of 10% to 400% for a period of 0.1 seconds to 24 hours. A typical orientation is an extension of 200% for a momentary period at room temperature. The elastic recovery of oriented blends of this invention is shown in Figure 7.

In one embodiment, articles can contain the composition of the invention after the composition has been oriented, and wherein the tension set from 200% extension equal to or less than $0.011M + 3$, preferably equal to or less than $0.0057M + 2$, more preferably equal to or less than $0.0035M + 1$, wherein M is 500% modulus expressed in lbs/inch^2 .

Annealing and orientation of the blend of the FPC and SPC lead to improvement in the tensile recovery properties of the blend. This is shown in the data in Tables below where the tension set recovery values for the blends described in the invention are described for the blends as made, after annealing and after orientation as described in the procedures above. The data show that the elastic recovery properties are enhanced.

Properties of the Blend: Flexural Modulus

The benefit of the above invention is that compositions comprising the FPC and the SPC containing optional amounts of process oil can be made which have low flexural modulus. These blends have a crystalline phase dispersed in the continuous crystallizable phase. The crystalline phase contains the majority of the FPC and some of the SPCs due to thermodynamic mixing while the continuous phase consists of the balance of the polymer blend. Low flexural modulus is a 1% secant modulus less than 60 kpsi in/in, more preferably less than 30 kpsi in/in and more preferably less than 15 kpsi in/in

These values of the flexural modulus over the range of composition of the FPC and SPC are dependent on the 500% tensile modulus. Flexural modulus of the blend is judged on two criteria: (a) extensibility to 500% elongation with a measurable modulus and (b) 1% secant flexural modulus. Comparative blends often cannot be extended to 500% extension for evaluation of the 500% modulus and thus cannot be compared to the blends of the current invention. The flexible blends of the current invention fulfill both of these conditions. Generally for all blends the flexural modulus deteriorates with increase in the 500% tensile modulus. Thus flexural modulus is judged relative to the tensile modulus of the blend for a 500% extension. The blends of the current invention have a lower flexural modulus, as indicated by low tension set, than blends of the comparative blends at comparable

500% tensile modulus. These properties are available over a wide range of composition and relative amounts of the FPC and the SPC. In the examples shown below we show examples of numerous blends of composition of the FPC and the SPC which have the above favorable combination of properties.

5 The dependence of the flexural modulus of the blend of this invention as a correlated function of the 500% tensile modulus is shown Figure 8.

 In one embodiment, the composition of the invention has a flexural modulus in kpsi.in/in equal to or less than $0.013M^{-1.3}$, preferably equal to or less than $0.0083M^{-1.6}$, more preferably equal to or less than $0.0062M^{-2.5}$ wherein M is
10 500% modulus expressed in lbs/inch^2 .

 In another embodiment, articles can contain the composition of the invention after the composition has been oriented, and wherein the flexural modulus in kpsi.in/in equal to or less than $0.013M^{-1.3}$, preferably equal to or less than $0.0083M^{-1.6}$, more preferably equal to or less than $0.0062M^{-2.5}$ wherein M is
15 500% modulus expressed in lbs/inch^2 .

 As used herein, Mooney Viscosity was measured as ML (1+4) at 125°C in Mooney units according to ASTM D1646.

 The composition of Ethylene propylene copolymers, which are used as comparative examples, was measured as ethylene Wt. % according to ASTM D
20 3900.

 The composition of the second polymer component was measured as ethylene Wt. % according to the following technique. A thin homogeneous film of the second polymer component, pressed at a temperature of about or greater than 150°C was mounted on a Perkin Elmer PE 1760 infra red spectrophotometer. A full
25 spectrum of the sample from 600 cm^{-1} to 400 cm^{-1} was recorded and the ethylene Wt. % of the second polymer component was calculated according to Equation 1 as follows:

$$\text{ethylene Wt. \%} = 82.585 - 111.987 X + 30.045 X^2$$

wherein X is the ratio of the peak height at 1155 cm^{-1} and peak height at either 722 cm^{-1} or 732 cm^{-1} , which ever is higher.

Techniques for determining the molecular weight (Mn and Mw) and molecular weight distribution (MWD) are found in U.S. Patent 4,540,753 (Cozewith, Ju and Verstrate) (which is incorporated by reference herein for purposes of U.S. practices) and references cited therein and in Macromolecules, 1988, volume 21, p 3360 (Verstrate et al) (which is herein incorporated by reference for purposes of U.S. practice) and references cited therein.

The procedure for Differential Scanning Calorimetry is described as follows. About 6 to 10 mg of a sheet of the polymer pressed at approximately 200°C to 230°C is removed with a punch die. This is annealed at room temperature for 240 hours. At the end of this period, the sample is placed in a Differential Scanning Calorimeter (Perkin Elmer 7 Series Thermal Analysis System) and cooled to about -50°C to about -70°C . The sample is heated at $20^{\circ}\text{C}/\text{min}$ to attain a final temperature of about 200°C to about 220°C . The thermal output is recorded as the area under the melting peak of the sample which is typically peaked at about 30°C to about 175°C and occurs between the temperatures of about 0°C and about 200°C is measured in Joules as a measure of the heat of fusion. The melting point is recorded as the temperature of the greatest heat absorption within the range of melting of the sample. Under these conditions, the melting point of the second polymer component and the heat of fusion is lower than the first polymer component as outlined in the description above.

Composition distribution of the second polymer component was measured by the thermal fractionation as described below. About 30 gms of the second polymer component was cut into small cubes about $1/8$ " on the side. This is introduced into a thick walled glass bottle closed with screw cap along with 50 mg of Irganox1076,

an antioxidant commercially available from Ciba - Geigy Corporation. Then, 425 ml of hexane (a principal mixture of normal and isomers) is added to the contents of the bottle and the sealed bottle is maintained at about 23°C for 24 hours. At the end of this period, the solution is decanted and the residue is treated with additional
5 hexane for an additional 24 hours. At the end of this period, the two hexane solutions are combined and evaporated to yield a residue of the polymer soluble at 23°C. To the residue is added sufficient hexane to bring the volume to 425 ml and the bottle is maintained at about 31°C for 24 hours in a covered circulating water bath. The soluble polymer is decanted and the additional amount of hexane is added
10 for another 24 hours at about 31°C prior to decanting. In this manner, fractions of the second polymer component soluble at 40°C, 48°C, 55°C and 62°C are obtained at temperature increases of approximately 8°C between stages. Further, increases in temperature to 95°C can be accommodated, if heptane, instead of hexane, is used as the solvent for all temperatures above about 60°C. The soluble polymers are dried,
15 weighed and analyzed for composition, as wt. % ethylene content, by the IR technique described above. Soluble fractions obtained in the adjacent temperature increases are the adjacent fractions in the specification above.

Comparative data was obtained with EPR which is Vistalon 457, sold by the Exxon Chemical Company, Houston TX.

20 Blends were made by mixing a total of 72g of all components, including the first polymer component, the second polymer component, the optional amounts of process oil and other ingredients in a Brabender intensive mixture for 3 minutes at a temperature controlled to be within 185°C and 220°C. High shear roller blades were used for the mixing and approximately 0.4g of Irganox-1076, an antioxidant
25 available from the Novartis Corporation, was added to the blend. At the end of the mixing, the mixture was removed and pressed out into a 6" x 6" mold into a pad 0.25" thick at 215°C for 3 to 5 minutes. At the end of this period, the pad was cooled

and removed and allowed to anneal for 1 day. Test specimens of the required dumbbell geometry were removed from this pad and evaluated on an Instron 4465 tester equipped with Instron Series IX Software for Windows to produce the mechanical deformation data. The Instron Tester and associated equipment is available from The Instron Corporation in Canton, MA. The testing was done at a travel rate of 20"/min and all data is reported in engineering stress and strain term with values of the stress uncorrected for the contraction in the cross section of the sample being tested.

Samples were aged by allowing them to stand at room temperature prior to testing. Samples were aged for 5, 10, 15, 20 and 25 days prior to testing on the Instron. Significant difference in the tensile strength and tension set were observed between samples aged 1 days versus those aged for 5 or more days. There was no experimental difference between samples aged 5 days or longer.

Samples were oriented by momentarily extending them to 200% extension at room temperature. These oriented samples were retested under tensile testing conditions outlined above. Tension set was determined on the samples of the blend which has been extended on the Instron tester to 200% extension and then allowed to relax. The samples were removed and the length (L2) of the deformation zone, between the grips on the Instron tester, was measured after 10 minutes. The original distance between the grips was the original length (L1) of the deformation zone. The tension set (TSet) is given by the formula

$$Tset = 100*(L2-L1)/L1$$

Flexural modulus was determined for samples of the blend by ASTM procedure D790 at room temperature.

The invention, while not meant to be limited thereby, is further illustrated by the following specific examples:

EXAMPLES

Example 1: Ethylene/propylene copolymerization to form the second polymer component.

Continuous Polymerization of the SPC was conducted in a 9 liter Continuous Flow Stirred Tank Reactor using hexane as the solvent. The liquid full reactor had a residence time of 9 minutes and the pressure was maintained at 700 kpa. A mixed feed of Hexane, ethylene and propylene was pre-chilled to approximately -30°C to remove the heat of polymerization, before entering the reactor. Solution of catalyst/activator in Toluene and the scavenger in hexane were separately and continuously admitted into the reactor to initiate the polymerization. The reactor temperature was maintained between 35 and 50 C, depending on the target molecular weight. The feed temperature was varied, depending on the polymerization rate to maintain a constant reactor temperature. The polymerization rate was varied from about 0.5 Kg/hr to about 4 Kg/hr.

Hexane at 30 Kg/hr was mixed with ethylene at 717 g/hr and propylene at 5.14 Kg/hr and fed to the reactor. The polymerization catalyst, dimethyl silyl bridged bis-indenyl Hafnium dimethyl activated 1:1 molar ratio with N', N'-Dimethyl anilinium-tetrakis(pentafluorophenyl)borate was introduced at the rate of 0.0135 g/hr. A dilute solution of triisobutyl aluminum was introduced into the reactor as a scavenger of catalyst terminators: a rate of approximately 111 mole of scavenger per mole of catalyst was adequate for this polymerization. After five residence times of steady polymerization, a representative sample of the polymer produced in this polymerization was collected. The solution of the polymer was withdrawn from the top, and then steam distilled to isolate the polymer. The polymerization rate was measured at 3.7 Kg/hr. The polymer produced in this polymerization had an ethylene content of 14%, ML (1+4) 125C of 13.1 and had isotactic propylene sequences.

Variations in the composition of the polymer were obtained principally by changing the ratio of ethylene to propylene. Molecular weight of the polymer was varied by either changing the reactor temperature or by changing the ratio of total monomer feed rate to the polymerization rate. Dienes for terpolymerization were added to the mixed feed stream entering the reactor by preparing the diene in a hexane solution and metering it in the required volumetric amount.

Example 2: Comparative ethylene/propylene polymerization where the propylene residues are atactic.

Polymerizations were conducted in a 1 liter thermostated continuous feed stirred tank reactor using hexane as the solvent. The polymerization reactor was full of liquid. The residence time in the reactor was typically 7 - 9 minutes and the pressure was maintained at 400kpa. Hexane, ethene and propene were metered into a single stream and cooled before introduction into the bottom of the reactor. Solutions of all reactants and polymerization catalysts were introduced continuously into the reactor to initiate the exothermic polymerization. Temperature of the reactor was maintained at 45°C by changing the temperature of the hexane feed and by using cooling water in the external reactor jacket. For a typical polymerization, the temperature of feed was about -10°C. Ethene was introduced at the rate of 45 gms/min and propene was introduced at the rate of 310 gms/min. The polymerization catalyst, dimethyl silyl bridged (tetramethylcyclopentadienyl) cyclododecylamido titanium dimethyl activated 1:1 molar ratio with N', N'-Dimethyl anilinium-tetrakis(pentafluorophenyl)borate was introduced at the rate of 0.002780 gms/hr. A dilute solution of triisobutyl aluminum was introduced into the reactor as a scavenger of catalyst terminators: a rate of approximately 36.8 mole per mole of catalyst was adequate for this polymerization. After five residence times of steady polymerization, a representative sample of the polymer produced in this polymerization was collected. The solution of the polymer was withdrawn from the

top, and then steam distilled to isolate the polymer. The rate of formation of the polymer was 258 gms/hr. The polymer produced in this polymerization had an ethylene content of 14.1 wt. %, ML@125 (1+4) of 95.4.

Variations in the composition of the polymer were obtained principally by changing the ratio of ethene to propene. Molecular weight of the polymer could be increased by a greater amount of ethene and propene compared to the amount of the polymerization catalyst. These polymers are described as aePP in the Tables below.

Example 3: Analysis and solubility of several second polymer components

In the manner described in Example 1 above, several second polymer components of the above specification were synthesized. These are described in the table below. Table 1 describes the results of the GPC, composition, ML and DSC analysis for the polymers.

TABLE 1

SPC	(Mn) by GPC	(Mw) by GPC	Ethylene wt. % by IR	Heat of fusion J/g	Melting Point by DSC (°C)	ML (1+4)@125°C
SPC-1	102000	248900	7.3	71.9	84.7	14
SPC-2			9.4	30.2	65.2	27.8
SPC-3	124700	265900	11.6	17.1	43.0	23.9
SPC-4			12.8	16.4	42.5	
SPC-5			14.7	13.2	47.8	38.4
SPC-6	121900	318900	16.4	7.8	40.3	33.1
SPC-7			17.8	5.3	39.5	
Comparative Polymers						
EPR			47.8	not detected	not detected	40
AePP			11.7	not detected	not detected	23

Table 1: Analysis of the second polymer component and the comparative polymers

Table 2 describes the solubility of the second polymer component

TABLE 2

SPC	Wt. % soluble at 23°C	Wt. % soluble at 31°C	Wt. % soluble at 40°C	Wt. % soluble at 48°C

SPC-1	1.0	2.9	28.3	68.5
SPC-3	6.5	95.7		
SPC-6	51.6	52.3	2.6	
SPC-5	36.5	64.2		
Comparative Polymers				
EPR	101.7			
aePP	100.5			

Table 2: Solubility of fractions of the second polymer component. Sum of the fractions add up to slightly more than 100 due to imperfect drying of the polymer fractions.

5 Table 3 describes the composition of the fractions of the second polymer component obtained in Table 2. Only fractions which have more than 4% of the total mass of the polymer have been analyzed for composition.

TABLE 3

SPC	Composition: Wt. % ethylene in fraction				
	soluble at 23°C	soluble at 31°C	soluble at 40°C	soluble at 48°C	soluble at 56°C
SPC-1			8.0	7.6	
SPC-3	12.0	11.2			
SPC-6	16.8	16.5			
SPC-5	14.9	14.6			
Comparative					
EPR	46.8				
Atactic ePP	11.8				

10 Table 3: Composition of fractions of the second polymer component obtained in Table 2. The experimental inaccuracy in determination of the ethylene content is believed to about 0.4 wt. % absolute.

Example 4:

Blends were made in all composition of Table 4 according to the procedure described above.

Sample	Wt % SPC1	ML of SPC1	C2 Wt. % of SPC1	500% Modulus		100% Modulus		Flexural modulus	
				(psi)	(MPa)	(psi)	(Mpa)	(kpsi in/in)	(MPa cm/cm)
F6	66.7	11.5	12.4	1778	12.26	1168	8.05		
F7	77.8	11.5	12.4	1442	9.94	813	5.61		
F8	88.9	11.5	12.4	1077	7.43	575	3.96		
F9	100	11.5	12.4	971	6.69	471	3.25		
G6	66.7	18.3	12.1	1800	12.41	1138	7.85		
G7	77.8	18.3	12.1	1446	9.97	741	5.11		
G8	88.9	18.3	12.1	1089	7.51	538	3.71		
G9	100	18.3	12.1	979	6.75	472	3.25		
H6	66.7	25.3	12.0	1969	13.58	1216	8.38	18.1	0.12
H7	77.8	25.3	12.0	1591	10.97	879	6.06	10.1	0.07
H8	88.9	25.3	12.0	1254	8.65	664	4.58	5.5	0.04
H9	100	25.3	12.0	1127	7.77	552	3.81	3.8	0.03
J6	66.7	39.7	13.4	1495	10.31	977	6.74		
J7	77.8	39.7	13.4	1394	9.61	754	5.20		
J8	88.9	39.7	13.4	904	6.23	452	3.12		
J9	100	39.7	13.4	751	5.18	320	2.21		
K5	55.6	28.9	14.8	1720	11.86	1297	8.94	23.1	0.16
K6	66.7	28.9	14.8	1471	10.14	990	6.83	7.7	0.05
K7	77.8	28.9	14.8	1251	8.63	621	4.28	3.9	0.03
K8	88.9	28.9	14.8	763	5.26	306	2.11	1.8	0.01
K9	100	28.9	14.8	387	2.67	200	1.38	1.3	0.01
L6	66.7	33.1	16.4	1133	7.81	613	4.23		
L7	77.8	33.1	16.4	704	4.85	293	2.02		
L8	88.9	33.1	16.4	573	3.95	187	1.29		
L9	100	33.1	16.4	91	0.63	96	0.66		
M6	66.7	25.6	17	996	6.87	597	4.12	4.2	0.03
M7	77.8	25.6	17	698	4.81	298	2.05	1.8	0.01
M8	88.9	25.6	17	336	2.32	185	1.28	1.0	0.01
M9	100	25.6	17	129	0.89	135	0.93	0.8	0.01
N8	88.9	34.5	11.1	1506	10.38	851	5.87		
N9	100	34.5	11.1	1412	9.74	675	4.65		
P8	88.9	16.4	10.8	1405	9.69	805	5.55	7.4	0.05
P9	100	16.4	10.8	1268	8.74	641	4.42	5.7	0.04

Table 4: Flexural Modulus, Tensile Modulus and Tension set for Binary Blends of one FPC and one SPC as molded

In this example blends of a First Polymeric Component, Escorene 4292, a homoisotactic polypropylene available from Exxon Chemical Co., Houston TX and one Second Polymeric component (identified as SPC1 in Table 4) were made using the procedure as described above. The blends were made in a different composition range as shown by the table above. All of the compositions are within have the properties of this invention. Properties of the blend were measured as molded.

Example 5:

Sample	Wt %	ML of	C2 Wt. %	Wt. %	500% Modulus		100% Modulus		Flexural modulus	
	SPC1	SPC1	of SPC1	SPC2	(psi)	(MPa)	(psi)	(Mpa)	(kpsi in/in)	(MPa cm/cm)
AA4	44.4	31.2	13.4	27.8	1833	12.64	1096	7.56	16.6	0.11
AA5	55.6	31.2	13.4	22.2	1571	10.83	909	6.27	11.3	0.08
AA6	66.7	31.2	13.4	16.7	1342	9.25	748	5.16	7.9	0.05
AA7	77.8	31.2	13.4	11.1	1077	7.43	524	3.61	4.7	0.03
AA8	88.9	31.2	13.4	5.56	872	6.01	385	2.65	3.4	0.02
AA9	100	31.2	13.4	0	751	5.18	320	2.21		
BB4	44.4	38.4	14.7	27.8	1791	12.35	1154	7.96	17.4	0.12
BB5	55.6	38.4	14.7	22.2	1543	10.64	798	5.50	13.8	0.10
BB6	66.7	38.4	14.7	16.7	1187	8.18	548	3.78	4.8	0.03
BB7	77.8	38.4	14.7	11.1	920	6.34	379	2.61	2.9	0.02
BB8	88.9	38.4	14.7	5.56	697	4.81	386	2.66	1.9	0.01
BB9	100	38.4	14.7	0	387	2.67	200	1.38		
CC5	55.6	24.9	12.1	22.2	1619	11.16	970	6.69	17.4	0.12
CC6	66.7	24.9	12.1	16.7	1504	10.37	849	5.85	12.1	0.08
CC7	77.8	24.9	12.1	11.1	1296	8.94	690	4.76	8.7	0.06
CC8	88.9	24.9	12.1	5.56	1152	7.94	581	4.01	5.8	0.04
CC9	100	24.9	12.1	0	1051	7.25	481	3.32	4.6	0.03
EE5	55.6	31.2	13.4	13.32	2019	13.92	1303	8.98		
EE6	66.7	31.2	13.4	10.02	1581	10.90	878	6.05		
EE7	77.8	31.2	13.4	6.66	1398	9.64	643	4.43		
EE8	88.9	31.2	13.4	3.33	1064	7.34	457	3.15		
EE9	100	31.2	13.4	0	871	6.01	381	2.63		
FF5	55.6	38.4	14.7	13.32	1830	12.62	1214	8.37	22.0	0.15
FF6	66.7	38.4	14.7	10.02	1612	11.11	847	5.84	8.4	0.06
FF7	77.8	38.4	14.7	6.66	1168	8.05	470	3.24	4.1	0.03
FF8	88.9	38.4	14.7	3.33	921	6.35	369	2.54	2.5	0.02
FF9	100	38.4	14.7	0	579	3.99	264	1.82	2.0	0.01
DD4	44.4	23.4	16.8	27.8	1640	11.31	1053	7.26	13.2	0.09
DD5	55.6	23.4	16.8	22.2	1424	9.82	708	4.88	6.2	0.04
DD6	66.7	23.4	16.8	16.7	1178	8.12	437	3.01	2.5	0.02
DD7	77.8	23.4	16.8	11.1	849	5.85	270	1.86	1.4	0.01
DD8	88.9	23.4	16.1	5.56	535	3.69	199	1.37	1.1	0.01
DD9	100	23.4	16.1	0	318	2.19	135	0.93		
GG6	66.7	24.9	12.1	10.02	1751	12.07	975	6.72		
GG7	77.8	24.9	12.1	6.66	1563	10.78	798	5.50		
GG8	88.9	24.9	12.1	3.33	1279	8.82	624	4.30		
GG9	100	24.9	12.1	0	1129	7.78	552	3.81		
HH5	55.6	23.4	16.8	13.32	1385	9.55	964	6.65	13.1	0.09
HH6	66.7	23.4	16.8	10.02	1005	6.93	501	3.45	4.0	0.03
HH7	77.8	23.4	16.8	6.66	531	3.66	251	1.73	1.9	0.01
HH8	88.9	23.4	16.8	3.33	318	2.19	184	1.27	1.1	0.01
HH9	100	23.4	16.8	0	129	0.89	135	0.93		
JJ6	66.7	31.2	13.4	3.33	1569	10.82	889	6.13		
JJ7	77.8	31.2	13.4	2.22	1303	8.98	603	4.16		
JJ8	88.9	31.2	13.4	1.11	1007	6.94	417	2.88		
JJ9	100	31.2	13.4	0	753	5.19	320	2.21		
KK5	55.6	38.4	14.7	4.44	1943	13.40	1316	9.07		
KK6	66.7	38.4	14.7	3.33	1666	11.49	871	6.01		
KK7	77.8	38.4	14.7	2.22	1295	8.93	507	3.50		
KK8	88.9	38.4	14.7	1.11	976	6.73	383	2.64		
KK9	100	38.4	14.7	0	387	2.67	200	1.38		
LL6	66.7	24.9	12.1	3.33	1944	13.40	1121	7.73		
LL7	77.8	24.9	12.1	2.22	1599	11.02	854	5.89		

LL8	88.9	24.9	12.1	1.11	1259	8.68	638	4.40		
LL9	100	24.9	12.1	0	1127	7.77	552	3.81		

Table 5: Flexural Modulus, Tensile Modulus and Tension set for Binary Blends of one FPC and two SPC as molded

In this example blends of a First Polymeric Component, Escorene 4292, a homoisotactic polypropylene available from Exxon Chemical Co., Houston TX and two Second Polymeric component (identified as SPC1 and SPC2 in Table 5) were made using the procedure as described above. The SPC2 has a ML(1+4)@125 of 14 and an ethylene content of 7.3 wt. %. The composition and the ML of the SPC1 are indicated in the Table for the various SPC1 used. The blends were made in a different composition range as shown by the table above. All of the compositions are within have the properties of this invention. Properties of the blend were measured as molded.

Example 6:

Sample	200% Hysteresis Set			Tension Set %		
	New	Annealed	Oriented	New	Annealed	Oriented
F6	55	56	31	28	27	6
F7	35	29	16	19	16	6
F8	20	24	15	16	9	6
F9	18	16	6	9	3	3
H6	65	64	31	34	31	13
H7	38	36	16	19	19	6
H8	33	25	16	16	13	3
H9	21	21	13	14	6	2
M5	91	71	54	42	31	16
M6	65	48	41	25	9	9
M7	38	28	29	9	6	3
M8	33	24	23	6	3	3
M9	32	19	20	9	3	2
N8	52	13	13	31	6	6
N9	57	33	32	38	16	19
P7	57	54	57	38	27	13
P8	39	34	34	25	22	10
P9	33	23	23	25	16	6
G6	60	56	31	28	25	13
G7	33	31	16	19	16	6
G8	24	28	8	13	9	3
G9	12	13	6	8	9	3
J6	47	21	21	19	9	9
J7	31	24	16	13	11	6
J8	18	13	7	13	9	6
J9	15	9	3	6	6	2
K5	71	79	48	34	41	16
K6	48	33	25	52	16	9
K7	19	15	11	9	9	2
K8	14	13	1	6	6	0
K9	16	8	6	5	3	0
L6	60	35	21	25	13	8
L7	39	20	14	9	3	5
L8	31	15	5	8	8	3
L9	31	31	9	9	0	3
AA4	65	54	43	33	28	14
AA5	40	39	20	25	19	8
AA6	27	31	16	22	16	5
AA7	19	19	11	16	13	5
AA8	17	14	13	13	9	2
BB4	53	56	35	28	28	9
BB5	37	36	19	19	19	6
BB6	23	15	16	14	9	6
BB7	14	20	5	11	6	5
BB8	14	18	10	9	6	3
CC5	58	49	30	34	25	16
CC6	43	41	20	22	16	8
CC7	29	24	15	19	13	6
CC8	28	20	11	17	9	6
EE5	60	56	60	31	42	11
EE6	35	26	35	17	14	6
EE7	21	14	21	13	9	5
EE8	16	14	16	9	6	2
FF4	88	81	64	50	38	25

FF5	52	48	31	30	23	13
FF6	23	23	15	13	9	6
FF7	19	11	5	9	6	3
FF8	9	8	5	6	3	2
DD4	65	56	39	31	23	6
DD5	34	34	26	16	25	6
DD6	28	23	20	11	17	3
DD7	24	23	20	9	13	3
DD8	28	24	15	6	9	0
GG6	43	43	43	25	25	9
GG7	28	28	28	19	16	9
GG8	22	22	22	16	13	6
HH4	79	79	54	45	41	19
HH5	64	64	39	34	28	11
HH6	38	34	26	16	11	5
HH7	28	30	21	9	6	2
HH8	26	25	15	6	3	0
JJ5	73	73	73	41	38	19
JJ6	35	35	35	19	16	8
JJ7	17	17	17	13	9	5
JJ8	13	13	13	9	6	5
KK5	56	64	39	31	28	11
KK6	30	26	19	17	13	5
KK7	18	11	9	9	6	2
KK8	11	12	6	9	6	2
LL6	60	60	60	34	31	13
LL7	32	32	32	19	16	8
LL8	26	26	26	16	13	6

Table 6: Hysteresis and Tension set for Binary Blends of one FPC and one SPC and Ternary Blend of one FPC and two SPC described in Table 4 and 5 as (1) new, (2) after annealing at room temperature for 21 days and (3) after momentary orientation to 200%.

5

Example 7:

Blends were made in all composition of Table 7 according to the procedure described above.

Sample	Wt % SPC1	Wt % FPC	500% Modulus		100% Modulus	
			(psi)	(MPa)	(psi)	(MPa)
2AA1	44.4	44.4				
2AA2	38.8	38.8				
2AA3	33.3	33.3				
2AA4	27.8	27.8	1302	8.98	919	6.34
2AA5	22.2	22.2	1194	8.23	794	5.47
2AA6	16.7	16.7	1013	6.98	604	4.16
2AA7	11.1	11.1	857	5.91	486	3.35
2AA8	5.55	5.55	690	4.76	353	2.43
2BB1	27	62				
2BB2	23	54				
2BB3	20	47				
2BB4	17	39	1311	9.04	994	6.85
2BB5	13	31	125	0.86	821	5.66
2BB6	10	23	1006	6.94	591	4.07
2BB7	7	16	823	5.67	438	3.02
2BB8	3	8	657	4.53	338	2.33

Table 7: Blends where the FPC is a reactor copolymer and the SPC are described below

In this example blends of a First Polymeric Component, Escorene 9272, a reactor copolymer available from Exxon Chemical Co., Houston TX having an ethylene content of 5 wt % and 2.9 MFR and two Second Polymeric component (identified as SPC1 and SPC2 in Table 7) were made using the procedure as described above. The SPC1 has a ML(1+4)@125 of 11 and an ethylene content of 14.5 wt %. The SPC2 has a ML(1+4)@125 of 21 and an ethylene content of 5.8 wt %. The blends were made in a different composition range as shown by the table above. All of the compositions are within have the properties of this invention. Properties of the blend were measured as molded.

Example 8:

Sample	200% Hysteresis Set			Tension Set %		
	New	Annealed	Oriented	New	Annealed	Oriented
2AA4	63	63	33	29	37	6
2AA5	39	39	28	20	22	9.
2AA6	31	29	15	17	16	3
2AA7	26	26	11	11	12	3
2AA8	18	15	9	8	9	3
2BB4	63	71	39	40	34	18
2BB5	44	43	28	37	19	12.
2BB6	26	31	15	12	12.	4
2BB7	19	20	11	9	11	3
2BB8	18	18	10	9	11	3

Table 8: Hysteresis and Tension set for Binary Blends of one FPC and one SPC and Ternary Blend of one FPC and two SPC described in Table 7 as (1) new, (2) after annealing at room temperature for 21 days and (3) after momentary orientation to 200%.

Example 9:

Blends were made in all composition of Table 7 according to the procedure described above.

Sample	Wt % SPC1	Wt % FPC	500% Modulus		100% Modulus	
			(psi)	(MPa)	(psi)	(MPa)
2CC1	44.4	44.4				
2CC2	38.8	38.8				
2CC3	33.3	33.3				
2CC4	27.8	27.8	1524	10.51	1082	7.46
2CC5	22.2	22.2	1261	8.69	733	5.05
2CC6	16.7	16.7	1119	7.72	581	4.01
2CC7	11.1	11.1	854	5.89	411	2.83
2CC8	5.55	5.55	656	4.52	304	2.10
2DD1	27	62				
2DD2	23	54				
2DD3	20	47				
2DD4	17	39	1647	11.36	1314	9.06
2DD5	13	31	1452	10.01	834	5.75
2DD6	10	23	1196	8.25	610	4.21
2DD7	7	16	885	6.10	388	2.68
2DD8	3	8	670	4.62	283	1.95

Table 9: Blends where the FPC is a reactor copolymer and the SPC are described below

In this example blends of a First Polymeric Component, Escorene 7132, a impact copolymer available from Exxon Chemical Co., Houston TX having an ethylene content of 9 wt % and 2.0 MFR and two Second Polymeric component (identified as SPC1 and SPC2 in Table 7) were made using the procedure as described above. The SPC1 has a ML(1+4)@125 of 11 and an ethylene content of 14.5 wt %. The SPC2 has a ML(1+4)@125 of 21 and an ethylene content of 5.8 wt %. The blends were made in a different composition range as shown by the table above. All of the compositions are within have the properties of this invention. Properties of the blend were measured as molded.

Example 10:

Sample	200% Hysterisis Set			Tension Set %		
	New	Annealed	Oriented	New	Annealed	Oriented
2CC4	66	77	39	37.5	34.375	14.0625
2CC5	44	41	28	23.4375	18.75	4.6875
2CC6	25	31	16	10.9375	9.375	3.125
2CC7	18	18	10	10.9375	9.375	3.125
2CC8	19	19	11	9.375	7.8125	1.5625
2DD4	89	89	58	53.125	34.375	25
2DD5	44	40	26	20.3125	18.75	6.25
2DD6	31	28	16	10.9375	10.9375	4.6875
2DD7	18	19	9	7.8125	7.8125	3.125
2DD8	21	19	11	4.6875	6.25	3.125

Table 10: Hysteresis and Tension set for Binary Blends of one FPC and one SPC and Ternary Blend of one FPC and two SPC described in Table 9 as (1) new, (2) after annealing at room temperature for 21 days and (3) after momentary orientation to 200%.

Example 11:

Blends were made in all composition of Table 11 according to the procedure described above.

Sample	Wt % SPC1	Wt % FPC	Wt % Sunpar 150	500% Modulus		100% Modulus	
				(psi)	(MPa)	(psi)	(MPa)
2EE1	36	36	20				
2EE2	31	31	20	1355	9.34	1130	7.79
2EE3	27	27	20	1248	8.60	945	6.52
2EE4	22	22	20	1119	7.72	749	5.16
2EE5	18	18	20	902	6.22	532	3.67
2EE6	13	13	20	690	4.76	336	2.32
2EE7	9	9	20	576	3.97	274	1.89
2EE8	4	4	20	386	2.66	176	1.21
2EE9	0	0	20	221	1.52	121	0.83
2FF1	21	50	20				
2FF2	19	44	20	1552	10.70	1313	9.05
2FF3	16	37	20	1442	9.94	1113	7.67
2FF4	13	31	20	1264	8.71	831	5.73
2FF5	11	25	20	1025	7.07	569	3.92
2FF6	8	19	20	798	5.50	387	2.67
2FF7	5	12	20	605	4.17	269	1.85
2FF8	3	6	20	406	2.80	176	1.21

Table 11: Blends where the FPC is an isotactic homopolymer, a process oil and the SPC are described below

In this example blends of a First Polymeric Component, Escorene 4292, a isotactic homopolymer available from Exxon Chemical Co., Houston TX having 0.9 MFR and two Second Polymeric component (identified as SPC1 and SPC2 in Table 7) were made using the procedure as described above. The SPC1 has a ML(1+4)@125 of 11 and an ethylene content of 14.5 wt %. The SPC2 has a ML(1+4)@125 of 21 and an ethylene content of 5.8 wt %. Sunpar 150 is a process oil available from Sun Refining Company. The blends were made in a different composition range as shown by the table above. All of the compositions are within have the properties of this invention. Properties of the blend were measured as molded.

Example 12:

Sample	200% Hysterisis Set			Tension Set %		
	New	Annealed	Oriented	New	Annealed	Oriented
EE3	58	58	43	31.25	28.125	10.9375
EE4	43	46	31	21.875	21.875	7.8125
EE5	36	36	21	15.625	17.1875	4.6875
EE6	25	26	15	10.9375	12.5	4.6875
EE7	18	19	11	7.8125	10.9375	4.6875
EE8	16	18	9	4.6875	7.8125	3.125
EE9	11	13	14	1.5625	4.6875	0
FF3	76	76	53	39.0625	37.5	15.625
FF4	58	53	36	28.125	26.5625	7.8125
FF5	38	38	29	15.625	17.1875	7.8125
FF6	29	24	21	10.9375	10.9375	6.25
FF7	20	19	11	7.8125	7.8125	3.125
FF8	16	18	11	6.25	6.25	3.125

Table 12: Hysteresis and Tension set for Ternary Blend of one FPC and two SPC and a process oil described in Table 11 as (1) new, (2) after annealing at room temperature for 21 days and (3) after momentary orientation to 200%.

Example 12: Comparative Blends

Comparative blends of compositions similar to those of the blends of the inventive composition were made with EPR and aePP as shown in Table 1. In all cases the blends had a tensile elongation less than 500% and are not reported in either the Figures 6, 7 and 8.

While the illustrative embodiments of the invention have been described with particularity, it will be understood that various other modifications will be apparent to and can be readily made by those skilled in the art without departing from the spirit and scope of the invention. Accordingly, it is not intended that the scope of the claims appended hereto be limited to the examples and descriptions set forth herein but rather that the claims be construed as encompassing all the features of patentable novelty which reside in the present invention, including all features which

would be treated as equivalents thereof by those skilled in the art to which the invention pertains.